

IN THE SPECIFICATION

Please replace Table 13 at page 30 with the following amended Table 13:

Table 13

Piezoelectric Ceramics	Pr Content (wt%)	Qmax (60MHz)
*Sample 11-1 <u>13-1</u>	0	5.9
Sample 11-2 <u>13-2</u>	0.02	6.5
Sample 11-3 <u>13-3</u>	0.05	6.7
Sample 11-4 <u>13-4</u>	0.10	6.5
Sample 11-5 <u>13-5</u>	0.12	6.1
*Sample 11-6 <u>13-6</u>	0.14	5.4

Sample with * mark deviates from the present invention.

Please replace Table 14 at page 32 with the following amended Table 14:

Table 14

Piezoelectric Ceramics	Ho Content (wt%)	Qmax (60MHz)
*Sample 12-1 <u>14-1</u>	0	5.9
Sample 12-2 <u>14-2</u>	0.02	6.3
Sample 12-3 <u>14-3</u>	0.05	6.6
Sample 12-4 <u>14-4</u>	0.10	6.3
Sample 12-5 <u>14-5</u>	0.12	6.1
*Sample 12-6 <u>14-6</u>	0.14	4.9

Sample with * mark deviates from the present invention.